

Technical Data Sheet

ED1226-9040

Laqva Prime

Product description

A high performance base coat for solid wood and board materials. Gives a very filled surface with low fibreswelling suitable for furniture and kitchen applications. To achieve best result two layers with good intermediate sanding should be applied. Fast drying and easy stackable

Product data

Solid content:	57 ±1	[weight %] theoretical
Specific gravity:	1410-1470	[kg/m³]
Viscosity:	34-40	[s] DIN 4
PH	7,5-9	test performed at 23 °C

Frost sensitive:	Yes
Storing incl transportation:	12 months
	At 5-30 °C

Process Temperature: 18-30 °C
To achieve the best result and consistency follow the application and surface temperatures given in Schedule of Application for each specific technology and production line.

Mixing/Application

Recommended application method	Hardener	Amount hardener [Parts by vol]	Dilutant	Application viscosity	Application amount [g/m²]	Notes
Air mix spraying			Water	delivered	100-180	
Air less spraying			Water	delivered	100-180	Paint pressure should be above 120 bar

Stir well before use!

Cleaning:	XX699
	Water

Drying

Method	Drying condition	Drying time	Notes
Forced drying	50 °C	10-15 min	depends on amount applied
Air Drying	20 °C	25-30 min	depends on amount applied

All kind of drying requires good ventilation and circulation

Do not stack before surface temperature below 30 °C

Exterior products: should not be exposed to water, water condensation or temperatures below 0 °C with in 48 h after application

Curing

UV-dose	Min UV dose [mJ/cm²]	Rec min Peak. [mW/cm²]	Min UV dose [mJ/cm²]	Rec min Peak. [mW/cm²]
	Hg lamps (280-320 nm)	Hg	Ga lamps (390-450 nm)	Ga
Full cure	N/A			
Semi cure	N/A			

Note - Required Peak/Energy is depending on several factors, such as substrate, amount of application, number of layers and type of UV oven / reflectors. Recommended application amounts and Peak/Energy values will be stated in the finishing instruction/process control submitted by technician.

General information

According to Swedish legislation we provide information regarding dangerous materials. The Safety Data Sheet contains facts about the components, primarily solvents and acids which present the dangerous characteristics. The Safety Data Sheet will be sent on request. All values and recommendations above are to be considered as guidance only. Many factors beyond our control may have an influence on the coating result. Should a problem arise, please contact us and we will advise accordingly. We reserve the right to alter the above specifications.

Date issued: **2020-02-04**

Latest update: 211123