

Technical Data Sheet

FONDO - AVORIO -

ED4601-9401

Description

Waterborne white one-component thixotropic sealer for exterior

Main use

Window frame, Wooden manufactured for exteriors.

Properties

Hiding power: very good

Anti-sagging properties: very good

Not yellowing the knots of pine

Blocking action against tannin oozing: excellent

Technical data

Viscosity	80 ± 10	s DIN 6 a 20°C
Density	1,23 (± 0,03)	kg/l
Flashpoint	non infiammabile/not flammable	Method: closed cup
Solid content (weight)	49 (± 2)	% by weight
Storage stability	15 months at 5°C ÷ 35°C	

Product preparation

Application	By spraying	
	% by weight	
Thinner	H ₂ O	5
Working temperature	5°C ÷ 35°C	coating, objects, air, substrate
Number of coats	1	
Suggested weight	150-200 g/m ²	

Technical information

	20°C	50°C
Dry to handle	2 h	
Drying	6 h	2 h
Sanding	24 h	8 h
Dry for overcoating	24 h	

Sherwin-Williams Italy S.r.l. - con unico socio

Sede legale ed Amministrativa: Via del Fifico, 12 - 40065 Pianoro (BO) - Italia - C.P. 18 - tel. +39 051 770 511 - fax +39 051 777 737 - servizioclienti@sherwin.com

Cod. Fisc. E Reg. Impr. Bo 08866930152 - P. IVA: IT 00494251200 - Cap. Soc. Euro 2.626.182 I.V. - Codice Mecc. Bo 014531

Società soggetta a direzione e coordinamento di: The Sherwin-Williams Company, USA

Special instructions

This insulating primer could be applied onto every impregnatin agent in our range. Apply about 200 micron wet

When it's dried sand with sandpaper grit 220-280

Once sanded it colud be finished with every top coat in our range

This insulating primer have excellent tannin blocker properties experimented on hard wood and exotics like oak,chestnut,mowingui, also on conifers like pine it gives very good properties against the knots yellowing defect. .

Check carefully the product before use, contact our technical service in case of problems

The product is sensitive to cold: keep it at temperatures from 5°C up.

FOR INDUSTRIAL USE ONLY

N.B.: Data provided on this technical data sheet correspond to our best knowledge and experience. we assure consistency on the chemical-physical characteristics of our products, within the tolerance limits specified in our technical data sheets. Responsibility of final result of product application is fully up to the users, who shall make sure that the product corresponds to their own needs with regard to application system, to substrates used as well as to working conditions.

Warning: actual viscosity of some pigmented and/or thixotropic products may differ from the viscosity shown on the technical data sheet. Differences are to be regarded as accetable if within 30% maximum.

Date: 07/2018

Sherwin-Williams Italy S.r.l. - con unico socio

Sede legale ed Amministrativa: Via del Fifico, 12 - 40065 Pianoro (BO) - Italia - C.P. 18 - tel. +39 051 770 511 - fax +39 051 777 737 - servizioclienti@sherwin.com

Cod. Fisc. E Reg. Impr. Bo 08866930152 - P. IVA: IT 00494251200 - Cap. Soc. Euro 2.626.182 I.V. - Codice Mecc. Bo 014531

Società soggetta a direzione e coordinamento di: The Sherwin-Williams Company, USA